

Timber Testing Compliance Report

Applicable Standard

AS/NZ 1604.1: 2021

Client	Porta Products Pty Ltd		Site	Porta Products Pty Ltd	
Address:	124 Lowes Mount Rd, Oberon,				
Plant No.	0	Charge No.	25274	Job Reference	78535
Preservative	Permethrin	Hazard Class	H 2	Species	Radiata Pine
Date Treated	13/08/2025	Date sampled	1/10/2025	Sample Type	X-Section
Product Description	252520904, 252250532, 252251103, 252251326, 252250733, 252520124, 252320906, 252522031, 252522311, 252312325, 252320131, 252321124			Reconstituted Wood	
				Various - Australia (All regions)	

Test Results

Test Type Sample	Retention Analysis Permethrin %m/m (Critical Level 0.0200)	Retention Analysis Outcome	Moisture Content g/100g as rcvd
1 252520904-22TT	0.0246	Pass	7.32
2 252250532-22TT	0.0240	Pass	6.92
3 252251103-19TT	0.0226	Pass	6.42
4 252251326-19TT	0.0227	Pass	6.47
5 252250733-22TT	0.0239	Pass	6.90
6 252520124-22TT	0.0237	Pass	7.20
7 252320906-19TT	0.0233	Pass	6.62
8 252522031-19TT	0.0205	Pass	6.99
9 252522311-19TT	0.0262	Pass	6.95
10 252312325-22TT	0.0224	Pass	6.26
11 252320131-22TT	0.0234	Pass	5.93
12 252321124-19TT	0.0248	Pass	6.24

Test Outcome

Samples 1–12 comply with the specifications for H 2 Permethrin treated Reconstituted Wood for use in Australia (All regions) as per AS/NZ 1604.1:2021

Method Summary

Test	Method Description	Standard/Reference
Retention Analysis	Submitted to RTH to analyse levels of Permethrin. For method refer to RTH report ref:	78535
Moisture Content	Submitted to RTH for moisture testing. For method refer to RTH report ref:	78535

Approved By:



Kieran Monaghan

Independent Verification Services

15 October 2025