


BORG Manufacturing - STRUCTAFLO - 2019 (Sprayed) - WET Sliptest Report - KO090519-2

09 May 2019

Slip Resistance Classification of New Pedestrian Surfaces - AS4586:2013 Appendix A

Date Tested:	09 May 2019
Test Report Number:	KO090519-2
Client Name & Address:	Borg Manufacturing - 2 Wella Way, Somersby New South Wales, 2250
Test Site / Project:	Sliptest Laboratory - Gaven
Surface / Product Tested:	STRUCTAFLO - 2019 (sprayed) - 5 pcs provided by client
Wet Pendulum Test carried out using :	Slider 96 (4S) Rubber slider
Record ambient temperature (°C)	24
Testing Officer :	Kathryn Ording - Munro-Stanley Portable Skid Tester #1133 - 30.08.17
Testing Officer Signature	

Test Results :

Sample No.	Swing 1	Swing 2	Swing 3	Swing 4	Swing 5	Mean BPN of last 3 swings :	Surface Picture
S1	50	50	50	49	49	49	
S2	55	55	54	54	54	54	
S3	55	55	54	54	54	54	
S4	55	53	52	52	52	52	
S5	55	55	51	51	51	51	

Mean BPN Slip Resistance Value (SRV)

52

CLASSIFICATION using Slider 96 (4S Slider)

P4 = 45 - 54

Accredited for Compliance with ISO/IEC 17025. The information presented herein and on the Sliptest Report is copyright and is protected by copyright law, any reproduction of this information and test report except in full is prohibited. Sliptest Australia Pty. Ltd. performed this on site test with reference to the following Australian Standard testing criteria, of AS 4586:2013 Classification of new pedestrian surface materials. Appendix A - Wet Pendulum Test Method and Hand Book HB 196: 2014 with reference to AS/NZS 4663: 2004 Slip Resistance measurement of existing pedestrian surfaces and HB 197: 1999. These results do not account for Future Wear, Maintenance or Contamination of this surface once in-situ.

Page 1 of 1 - END OF REPORT